

# Technical Data Sheet



## Product name: EasyFil™ PLA

Date of issue: 29 October 2015

Version: v2

EasyFil™ PLA is an “easy to use” high-end PLA (Poly-Lactic Acid ) type of 3D printer filament. With retaining the typical PLA features, EasyFil™ PLA is slightly modified with an impact modifier, making the filament tougher, less rigid, slightly softer and therefore “easy to print” at relatively low temperatures. By being slightly modified, EasyFil™ PLA is much longer preservable than normal PLA.

Another great advantage of EasyFil™ PLA - compared to regular PLA - is EasyFil™’s low shrinkage factor, which makes EasyFil™ PLA nearly warp-free and therefore EasyFil™ PLA will not deform after cooling.

Properties	Typical value	Test Method	Test condition
<b>Physical</b>			
Specific gravity	1.24 g/cc	ASTM D1505	-
Melt flow rate	6.0 g/10min	-	-
Water absorption	-	-	-
Moisture absorption	-	-	-
<b>Mechanical</b>			
Impact strength	7.5 KJ/m <sup>2</sup>	-	-
Tensile strength	110 Mpa (MD)	ASTM D882	-
Tensile modulus	3310 Mpa (MD)	ASTM D882	-
Elongation at break	160% (MD)	ASTM D882	-
Flexural strength	± 55.2 Mpa	-	-
Flexural modulus	± 2392.5 Mpa	-	-
Hardness	-	-	-
<b>Thermal</b>			
Print temperature	± 180 - 220° C	-	-
Melting temperature	± 210 ± 10° C	-	-
Viscat softening temp.	± 60° C	ISO 306	-
<b>Optical</b>			
Haze	2.1%	ASTM D1003	-
Transmittance	-	-	-
Gloss	90	ASTM D1003	Gloss, 20°

Product details, certifications and compliance	Diameter	Tolerance	Roundness	
HS Code	39169090	1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes			
FDA compliant	Yes			

Formfutura VOF	CoC: 55502105	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL851741083B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL851741083	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.